

# FiberPlast®

## SPECIFICATIONS

<u>PROPERTY</u>	<u>TYPICAL VALUE</u>	<u>ASTM TEST METHOD</u>
Melt Index 190°C/2.16g/10 min	.10-.35	D1238
Density g/cc	.93-.955	D1505
Tensile Strength @ Yield psi	2000-4000	D638
Elongation %	>800	D638
Cold Crack Temperature	-42°C	D746
Flexural Modulus psi	20,000	D790
Environmental Stress Cracking F <sub>50,h</sub>	45	D1693

*FiberPlast® is a utility blend and values may vary from run to run*

NOTE: While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation or warranty, express or implied, as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any, of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights and responsibility and liability therefore is disclaimed.

**B&F PLASTICS**  
INCORPORATED

[www.bfplastics.com](http://www.bfplastics.com)

540 N. 8 St., Richmond, IN 47374  
765-962-6125, 800-562-8365  
FAX 765-962-7170